



StoCretec GmbH  
Report No. ST 2601-1714  
Cleanroom (atmospheric)

# Cleanroom<sup>®</sup> Suitable Materials

StoFloor Cleanroom System 2  
H<sub>2</sub>O<sub>2</sub> Absorption/Desorption:  
non-absorptive

FLOORING & COATING

DUPLICATE

Single product | Einzelprodukt  
Hydrogen Peroxide  
Absorption/Desorption  
Wasserstoffperoxid  
Absorption/Desorption

# Statement of Qualification · Single product

## Qualifizierungsbescheinigung · Einzelprodukt

### Customer

Auftraggeber

StoCretec GmbH  
Gutenbergstrasse 6  
65830 Kriftel  
Germany

### Material tested

Untersuchter Werkstoff

StoFloor CR System 2 (StoPox GH 205; StoPox KU 601) (RAL 7035)  
For the specific product data such as manufacturing date and serial number please refer to the test report.  
Produktspezifische Daten wie Herstellungsdatum und Seriennummer sind dem Prüfbericht zu entnehmen.

### Hydrogen peroxide absorption/desorption

Wasserstoffperoxid Absorption/Desorption

Standards/Richtlinien:  
Standards/Richtlinien:

VDI 2083 Part|Blatt 20  
The norms stated generally refer to the version valid at the time of the tests.  
Die angegebenen Normen beziehen sich generell auf die zum Zeitpunkt der Untersuchungen gültige Fassung.

Test environment parameters:  
Testparameter der Prüfumgebung:

Temperature|Temperatur: .....22°C ± 0.5°C

Test procedure parameters:  
Testparameter der Versuchsdurchführung:

- Emission test cell volume|Volumen der Emissionsprüfzelle:..... 16.5 cm<sup>3</sup>
- Exposed surface area|Exponierte Oberfläche:..... 33 cm<sup>2</sup>
- Hydrogen peroxide vapor concentration|Konzentration:.....50 ± 20 ppm (V)
- Exposure duration|Expositionsdauer:..... 60 min
- Air exchange rate during aeration: .....  
Luftwechselrate während der Belüftung: ..... 100 min<sup>-1</sup>

### Test result / Classification

Untersuchungsergebnis/Klassifizierung

The hydrogen peroxide absorption/desorption of StoFloor CR System 2 (StoPox GH 205; StoPox KU 601) was investigated with the stated test parameters. Using the procedure laid down in VDI 2083 Part 20, the following test result were obtained:  
Bei der Bestimmung des Absorptions-/Desorptionsverhaltens von Wasserstoffperoxid des StoFloor CR System 2 (StoPox GH 205; StoPox KU 601) konnte folgendes Ergebnis gemäß VDI 2083 Blatt 20 festgestellt werden:

Ø k-value Ø k-Wert [min]	Standard deviation Standardabweichung [min]	Classification Klassifizierung
4.77	0.83	<b>non-absorptive</b> <b>nicht-absorptiv</b>

The k-value represents the required decay time to reduce the hydrogen peroxide vapor concentration measured at the beginning of the aeration phase to one tenth of the original concentration. The mean k-value can only be used to compare different materials and is transferred to the following classification:

Der k-Wert stellt die Abklingzeit dar, in welcher die gemessene maximale Wasserstoffperoxid-Konzentration zu Beginn der Belüftungszeit auf ein Zehntel des initialen Werts reduziert wird. Der gemittelte k-Wert kann nur für eine vergleichende Materialbewertung herangezogen werden und wird in folgende Klassifizierung überführt:

- ≤ 5 min: ..... non-absorptive | nicht-absorptiv
- > 5 - ≤ 15 min: ..... fast | schnell
- > 15 - ≤ 60 min: ..... medium | medium
- > 60 min: ..... slow | langsam
- Not determinable|nicht bestimmbar: ..... catalytic activity  
..... katalytische Aktivität

The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

Detailed information and parameters of the test environment can be found in the Fraunhofer IPA test report.

Die für die Qualifizierung verwendeten Messeinrichtungen werden regelmäßig kalibriert und sind auf nationale und internationale Standards rückführbar. Sofern keine nationalen Standards existieren, entspricht das Messverfahren den derzeit gültigen technischen Regeln und Normen. Die Dokumentation kann bei Bedarf eingesehen werden.

Detaillierte Informationen sowie die Parameter der Prüfumgebung entnehmen Sie bitte dem Prüfbericht des Fraunhofer IPA.

Fraunhofer Institute for Manufacturing  
Engineering and Automation IPA

ST 1902-1095  
Report No. first document

Stuttgart, February 28, 2019  
Place, date of first document issued

Business unit  
Testing and Certification

ST 2601-1714  
Report No. current document

Stuttgart, May 6, 2026  
Place, current date

Nobelstrasse 12  
70569 Stuttgart  
Germany

on behalf of   
Dr.-Ing. Frank Bürger, head of business unit Testing and Certification